



VERTRO

PLASTICISING AND TROPICALISATION VARNISH

**PERMEATES ALL POROUS PARTS
LONG-TERM PROTECTION OF METALS**

DEFINITION

Plasticising and tropicalisation varnish. Protects parts by insulating them against humidity. Formulated for protecting printed circuit boards, and other electronics subjected to corrosive environments, cases, windings, connections, etc.

Use also to permeate porous materials and to protect metals subjected to corrosive environments.

ADVANTAGES

Resists UV rays well; does not turn yellow.
Bonds perfectly with all metals.
Resists mineral and synthetic oils extremely well.
Protects against hydrocarbons.
Demonstrates excellent coverage.
Guaranteed silicone-free.

APPLICATION FIELDS

Protecting printed circuit boards, electronic and mechanical devices.
Protecting documents, plastics, cards, etc.
Offers long-lasting protection against corrosion, scratches, and graffiti.
Stops ladders in textiles...
Protects against aggressive environments: humidity, salt spray, cold, heat, UV rays, industrial atmospheres, etc.

In bulk, product can be applied in a bath or with a brush as a permeating varnish to seal the pores of all alloys, metals, Bakelite, and ceramics.

TECHNICAL CHARACTERISTICS

Aspect Very shiny
Colour Colourless
Drying time 3 minutes minimum
..... 15 minutes maximum,
..... depending on the temperature and thickness of coating

1/2

Manufacturing site and registered office

Parc Industriel de la Plaine de l'Ain - 225 allée des Cèdres - 01150 Saint-Vulbas - FRANCE
Tél. +33 (0)4 74 40 20 25 - Fax +33 (0)4 74 40 20 26 - www.orapi-maintenance.com

ORAPI® cannot be expected to know all applications in which its products are used or their conditions of use. ORAPI® shall not be held responsible: for the suitability of its products for a given use or specific purpose, for the methods of application over which it has no control. The information contained in this technical data sheet can on no account be a substitute for the preliminary tests which are essential and which must be carried out in order to check the suitability of the product to each intended application. The user of the product described in this technical data sheet is solely responsible for all measures required to protect people and property from hazards that may arise from the implementation and/or use of this product. Therefore, ORAPI® renounces any implicit or explicit guarantees, including guarantees relating to marketability or suitability for a certain purpose, resulting from the sale or use of its products. In particular, ORAPI® renounces any claims for incidental or consequential damages whatsoever, including financial operating losses.

TECHNICAL CHARACTERISTICS - continued

Durability of treatment	1 year in normal environment
Dielectric constant	100 KV/mm
Non-volatile matter	>15%
Operating temperature	-40°C to +140°C

INSTRUCTIONS FOR USE

Clean parts to be treated. Then spray VERTRO onto the surface from 15 to 30 cm away, apply by brushing or by soaking.

Clean with ORAPI solvent NDI.

PACKAGING

650 ml aerosol	Ref. 4715 A4	x 12
5 L jerry-can	Ref. 2715 J1	x 4